K 420
Gümüş Alaşımlı Kadmiyumlu Sert Lehim Telleri

Mekanik ve fiziksel özellikler		
Erime Aralığı	C°	610/620
Çalışma Sıcaklığı	C°	620
Gerilme direnci	Mpa	-
Elektiriksel iletkenlik	% IACS	-
Yoğunluk	gr/cm³	-
Uzama Katsayısı	%	-

Spesifikasyonlar		
EN ISO 17672		-
DIN 8513		-
AWS A5.8		-
DIN EN 1044		AG 303
EN ISO 3677		-

Ana elementler %(min-max)
Ag : 41-43 / Cd : 23-27 / Zn : 14-18 / Cu : 16-18

Diğer %
Impurity : 0,15 max

Uzama Katsayısı %
-

RoHS Limit ppm
N/A

Availability							
Çubuk Tel	Kaplanmış Tel	Kangal / Tel	Yassı Levha	Preform	Toz	Macun	FW
●	●	●	○	●	○	○	●

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.
Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004
www.asakaynak.com
info@asakaynak.com