# T 260
## Gümüş Alaşımlı Kadmiyum İçermeyen Sert Lehim Telleri

| Mekanik ve fiziksel özellikler | | |
|---|---|---|
| Erime Aralığı | C° | 705/800 |
| Çalışma Sıcaklığı | C° | 800 |
| Gerilme direnci | Mpa | - |
| Elektiriksel iletkenlik | % IACS | - |
| Yoğunluk | gr/cm³ | - |
| Uzama Katsayısı | % | - |

| Spesifikasyonlar | | |
|---|---|---|
| EN ISO 17672 | | Ag 425 |
| DIN 8513 | | - |
| AWS A5.8 | | B-Ag26 |
| DIN EN 1044 | | - |
| EN ISO 3677 | | B-Cu38ZnAgNiMn |

| Ana elementler %(min-max) |
|---|
| Ag : 24-26 / Cu : 37-39 / Zn : 31-35 / Ni : 1,5-2,5 / Mn : 1,5-2,5 |

| Diğer % |
|---|
| Impurity : 0,15 max |

**Uzama Katsayısı %**
-

**RoHS Limit ppm**
Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

| Availability | | | | | | | |
|---|---|---|---|---|---|---|---|
| Çubuk Tel | Kaplanmış Tel | Kangal / Tel | Yassı Levha | Preform | Toz | Macun | FW |
| ● | ● | ○ | ○ | ○ | ○ | ○ | ○ |

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

**ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.**
Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004
www.asakaynak.com
info@asakaynak.com