CUP 810 SF

Kıvılcım Yapmayan Bakır-Fosfor Telleri

Mekanik ve fiziksel özellikler

Erime Aralığı	C°	710-750
Çalışma Sıcaklığı	C°	720
Gerilme direnci	Mpa	
Elektiriksel iletkenlik	% IACS	-
Yoğunluk	gr/cm³	-
Uzama Katsayısı	%	

Spesifikasyonlar

EN ISO 17672		CuP 182
DIN 8513		L-CuP8
AWS A5.8		-
DIN EN 1044		CP 201
EN ISO 3677		B-Cu92P-710/750

Ana elementler %(min-max)

P: 7,6-8,0 / Cu: Bal.

Diğer %

Impurity : 0,25 max

RoHS Limit ppm
Cd (100ppm) ; Pb / Hg / Cr (1000ppm)

Availability

Çubuk Tel	Kaplanmış Tel	Kangal / Tel	Yassı Levha	Preform	Toz	Macun	FW
●	○	●	○	●	○	○	●

Liability - Disclaimer: This document is intended to assist the user in choosing the product. We provide these results in all conscience; this not however exempting the consumer from the obligation to check our products and process on his own responsibility, including suitability, compliance with applicable law and non-infringement of the rights of others. The company ASA KAYNAK cannot be held liable in respect thereof.

ASA KAYNAK ve METAL ALAŞIMLARI SAN. ve TİC. A.Ş.
Veliköy OSB Sanayi Mahallesi 22. Cad. 4/A
Veliköy / Çerkezköy / Tekirdağ / Turkey 59500
Phone: +90 282 746 1004
www.asakaynak.com
info@asakaynak.com